

# PRODUCT SHEET

## SMOOTH MATT WEATHERPROOF COATING (EM22)

### Product information

#### DESCRIPTION

An advanced, water-borne, smooth, matt finish for masonry surfaces. Formulated for exceptional durability and weather resistance.

#### USAGE/PUPOSE

For external use on smooth or textured cement render, plaster, brickwork, blockwork, asbestos cement, pebbledash and other masonry surfaces.

#### CHARACTERISTICS

- Moisture vapour permeable
- Environmentally friendly, water-borne formulation
- Good alkali resistance

#### PERFORMANCE

- Exceptionally durable and weather resistant
- Will provide at least 12 years protection (when applied correctly on sound substrates)
- High opacity
- Very good adhesion to general masonry surfaces
- Minimal dirt retention
- Blister proof

#### FINISH

Smooth, matt finish.

#### COLOUR

White, black and 40 colours.

#### ENVIRONMENTAL CONSIDERATIONS

Water-borne. Contains no added lead.

#### PACKAGING

**Can sizes:** 5 litres.

#### AVAILABILITY

Available from RHINOCEROS Limited.  
Tel: 0208 444 6165.

### Technical specification

#### COMPOSITION

High performance water based resin. With organic and inorganic pigments as colouring agents.

NB: This product contains a fungicide/algaeicide for the sole purpose of protecting the film

#### Surface preparation

Remove all flaking and loose material back to a sound surface. Make good any defective surfaces and leaking rainwater goods. Ensure all surfaces are clean, dry and firm.

#### If there is organic growth:

Remove with a stiff bristle (not wire) brush and apply a liberal coat of Glixtone Fungicidal Wash: GS37

#### If the surface is chalky or friable:

Apply Glixtone Weatherproof Stabilising Solution SS01

#### Application

#### METHOD

Stir thoroughly before use. Apply 2 coats by brush, roller or spray.

#### RECOMMENDED FILM THICKNESS

**Wet:** 110 microns

**Dry:** 35 microns

#### THINNING

Do not thin. Use straight from can.

#### COVERAGE

Dependent upon the porosity and texture of the substrate. Average 9m<sup>2</sup> per litre, per coat. (10m<sup>2</sup> per litre on smooth surfaces of average porosity).

#### DRYING TIME

Dependent upon weather conditions and average temperature. Usually touch dry and re-coatable in 2-4 hours. Drying will be slower in conditions of high humidity.

## CLEANING

Clean all brushes, rollers and spray equipment with water immediately after use.

## LIMITATIONS

DO NOT apply

- when there is a risk of rain or frost
- during excessively damp conditions
- when the temperature is below 5°C

## Health and safety notes

Detailed information and guidance is provided in Product Safety Data Sheet EM22. The following represents important selected information only:

- Ensure good ventilation during application and drying
- Avoid contact with eyes and skin

### In case of contact with eyes:

Rinse immediately with plenty of water and seek medical advice.

### In case of contact with skin:

Wash immediately with plenty of soap water or a proprietary skin cleanser.

### When spraying

- Do not breathe spray
- Wear suitable respiratory protective equipment

KEEP OUT OF REACH OF CHILDREN

## STORAGE

Store in secure, dry conditions at temperature between 5°C and 28°C. Protect from frost. Containers should be kept closed during storage. Avoid spillage and contamination. Do not empty into drains and water courses.

## SHELF LIFE

1 year in original, unopened container, if stored in accordance with recommendations above.

## Additional information

### TECHNICAL ASSISTANCE

For further information, advice or guidance regarding any aspect of our products, please contact us at the address below.

### REFERENCES

See also:

- Product Safety Data Sheet EM22

### WARRANTY

As we have no direct control over the methods employed by the user in applying its products, any warranty, either written or implied, is given in good faith and can only cover the material itself.

### Contact us

RHINOCEROS Limited  
Huntingdon Works  
Huntingdon Road  
East Finchley  
London N2 9DX

t. +44 (0)208 444 6165

f. +44 (0)208 365 2865

e. [contracts@rhino247.co.uk](mailto:contracts@rhino247.co.uk)

w. [www.rhino247.co.uk](http://www.rhino247.co.uk)